




















	Standard	Result
 Size		1500,0 X 250,0
 Thickness		4,5 mm
 Wear layer		0,55 mm
Surface treatment		K-Guard+ PU coating
Guarantee	Light industrial	10 years
	Commercial	12 years
	Domestic	15 years
 Bevelled edge		No
 Standards	EN 649	Heterogeneous PVC
 Classification	EN 685- Light industrial	42: Light industrial general
	EN 685- Commercial	33: Commercial heavy
	EN 685- Domestic	23: Domestic heavy
 Reaction to fire	EN 13501-1	B _{f1} -s1
	EN ISO 9239-1	Pass
	EN ISO 11925-2	Pass
 Staining resistance	EN 423	Class 0
 Light fastness	EN ISO 105-B02	≥7
 Abrasion resistance	EN 660-2	Group T
 Dimensional stability	EN 434	≤ 0,10%
 Acoustic Impact noise reduction	EN ISO 717-2 / EN ISO 140-8	ΔL _w = 13 dB
 Electrical behaviour body voltage	EN 1815	Pass
 Indentation - residual	EN 433	≤ 0,1 mm
 Castor chair continuous use	EN 425	Pass
 Mass per unit area	EN 430	7082 g/m ²
Thermal conductivity	ISO 8302	0,0245 m ² K/W
		Suitable for underfloor heating. Max 27°C
**Slip resistance	DIN 51130	R10
	DIN 51097	B
	EN 13893	DS
 Adhesive		Most applications will not require the use of adhesives. However, we recommend the use of a tackifier for heavy traffic areas.
 Recycling		Suitable
 VOC emission	French VOC regulation (ISO 16000)	A+

**Slip resistance is measured on ex-factory product. Slip resistance in use will depend on how the product is maintained

For more information:

Designflooring - T: +44 (0)1386 820105 | F: +44 (0)1386 820132

Designflooring SAS - T: 01 57 32 39 13 | F: 01 57 32 39 14

Designflooring GmbH - T: 0211 469 59203 | F: 0211 469 59204

Designflooring Nederland - T: 020 200 8282 | F: 020 200 8386

e: info@designflooring.com

www.designflooring.com

